

Review

A review on antimicrobial properties of nano-ferrites: Biomedical applications

G. M. Shweta^{1,*}, Lalsingh Naik², Sushant Kakati³, Rangappa Pujar⁴, Shridhar Mathad^{3,*}, Deepak Shirgaonkar⁵¹ Department of Physics, K.R.Pete Krishna Government Engineering College, Krishnarajapete, Karnataka 571426, India² Department of Physics, Karnatak University, Dharwad, Karnataka 580001, India³ Department of Engineering Physics, K.L.E.Institute of Technology, Hubli, Karnataka 58027, India⁴ Department of Physics, P.C. Jabin College, Hubli, Karnataka 580020, India⁵ Department of Physics, Anandibai Raorane Arts, Commerce and Science College, Vaibhavwadi, Dist Sindhudurg, Maharashtra 416810, India* **Corresponding authors:** G. M. Shweta, shwetagm01@gmail.com; Shridhar Mathad, physicssiddu@kleit.ac.in

CITATION

Shweta GM, Naik L, Kakati S, et al. A review on antimicrobial properties of nano-ferrites: Biomedical applications. *Characterization and Application of Nanomaterials*. 2025; 8(1): 7509. <https://doi.org/10.24294/can7509>

ARTICLE INFO

Received: 27 June 2024

Accepted: 29 October 2024

Available online: 22 November 2024

COPYRIGHT



Copyright © 2024 by author(s). *Characterization and Application of Nanomaterials* is published by EnPress Publisher, LLC. This work is licensed under the Creative Commons Attribution (CC BY) license. <https://creativecommons.org/licenses/by/4.0/>

Abstract: This review focuses on ferrites, which are gaining popularity with their unique properties like high electrical resistivity, thermal stability, and chemical stability, making them suitable for versatile applications both in industry and in biomedicine. This review is highly indicative of the importance of synthesis technique in order to control ferrite properties and, consequently, their specific applications. While synthesizing the materials with consideration of certain properties that help in certain methods of preparation using polyol route, green synthesis, sol-gel combustion, or other wise to tailor make certain properties shown by ferrites, this study also covers biomedical applications of ferrites, including magnetic resonance imaging (MRI), drug delivery systems, cancer hyperthermia therapy, and antimicrobial agents. This was able to inhibit the growth of all tested Gram-negative and positive bacteria as compared with pure ferrite nanoparticles without Co, Mn or Zn doping. In addition, ferrites possess the ability to be used in environmental remediation; such as treatment of wastewater which makes them useful for high-surface-area and adsorption capacity due heavy metals and organic pollutants. A critical analysis of functionalization strategies and possible applications are presented in this work to emphasize the capability of nanoferrites as an aid for the advancement both biomedical technology and environmental sustainability due to their versatile properties combined with a simple, cost effective synthetic methodology.

Keywords: nano-ferrites; ferrites; dopants; biomedical

1. Introduction

Human development is the epicenter of all study through the use of resources and the creation of new chemicals that benefit society. In particular, magnetic materials have grown in significance, and now, these are widely employed in many different sectors because of their unique properties; these properties are used in many fields, such as the chemical industry, the medical field, and electronics [1]. When pure metals are compared with ferrite materials, which are known as magnetic materials due to their special properties, this includes low cost, high resistance, and simple production processes. In ferrites, ferric oxides are the main components, which are a mixture of other metal oxides; these ferrites can be synthesized by using hematite (Fe₂O₃) or magnetite (Fe₃O₄) and are typically non-conducting [2].

The characteristics of structural, electrical and magnetic are greatly improved by substituting tiny quantities of dopants, which makes ferrites appropriate for many

technological applications [3]. The production of nanoferrites has received great interest which is due to their improved magnetic and electrical characteristics and this is easy comparable bulk counterparts [4,5]. These ferrites useful for different field due their improved magnetic characteristics which is in nanoscale in size, and also contain lager surface to volume ratio and quantum confinement effect [6]. This result indicates that nanoferrites is a essential materials for industry and technology, propelling breakthroughs in electronics, telecommunications, and healthcare. High magnetic permeability, chemical and thermal stability, high electrical resistivity, and gentle magnetic behavior are just a few of the remarkable qualities that ferrites have. These characteristics make them extremely adaptable for a different application, which includes choke coils, Ferrites are utilized across a range of applications due to their unique properties. In microwave frequency devices, they exhibit high permeability ($\mu > 1000$) and low loss tangents ($\tan \delta < 0.1$), facilitating efficient signal transmission. In computer memory core elements, magnetic saturation (50–80 emu/g) and moderate coercivity ($H_c \sim 20\text{--}300$ Oe) ensure reliable data storage and retrieval. For biomedical applications, surface-coated ferrites (PEG or silica) with particle sizes of 10–100 nm enhance biocompatibility and cellular uptake. They also show promise in hyperthermia treatments with a specific absorption rate (> 100 W/g) and smaller particle sizes (10–50 nm) for effective heat generation. In drug delivery, ferrites allow for targeted therapy through magnetic saturation (50–80 emu/g) while maintaining biocompatibility. Their antibacterial and antifungal efficacy is supported by small particle sizes (10–50 nm) and functionalization with antimicrobial agents, ensuring chemical stability across various pH ranges. Lastly, in water treatment, nano-sized ferrites (10–200 nm) with magnetic saturation (50–70 emu/g) and a surface area of 50–150 m²/g enable efficient, transformer cores, antenna rods, gas sensors, recording heads, electrodes telecommunication systems, and biomedical applications like drug delivery, magnetic hyperthermia, and magnetic resonance imaging [7–9]. The electrical and magnetic characteristics work together to provide substantial performance and efficiency gains, making them widely used in contemporary electronics and healthcare systems [10–12].

This review article starts a discussion of different synthesis methods for ferrites, their antibacterial characteristics, and their prospective uses in biomedicine. In specific condition the dopants to the improvement of their characteristics are discussed, along with the difficulties and prospects associated with the switch from bulk to nano-ferrites for next-generation technological advancements.

2. Synthesis of ferrites

The synthesis methods of ferrites are critically important because the properties and applications of ferrites are highly dependent on their synthesis techniques. The choice of synthesis method influences the size, shape, purity, crystallinity, magnetic properties, and surface characteristics of the ferrite nano-particles. These factors, in turn, determine the material's suitability for specific applications, such as in electronics, catalysis, medical devices, and environmental remediation. Many synthesis techniques is Shown in **Figure 1** like Ball milling, Solid state reaction method, Coprecipitation method, Hydrothermal, Micro-emulsion techniques are used

to synthesize ferrite materials [13–16]. Different approaches like Polyol technique, Green Synthesis technique, Sol gel method, Sol gel auto-combustion Fast firing method (Pramanik Method) etc., are employed to prepare ferrites [15–23].




Figure 1. Synthesis techniques of ferrites.

Table 1. Different synthesis methods of ferrites.

Method	Description	Key Features	Typical Conditions
Solid-State Reaction	Mixing metal oxides or carbonates followed by high-temperature sintering.	Simple, cost-effective, suitable for bulk synthesis	High temperatures (1000–1400 °C), long sintering times (4–8 h)
Sol-Gel Method	Using metal alkoxides or nitrates to form a gel, followed by drying and calcination.	High purity, fine particle size, homogeneity	Low to moderate temperatures (400–800 °C), controlled atmosphere
Co-precipitation	Precipitating metal hydroxides from a solution, followed by drying and calcination.	Uniform particle size, suitable for nanoparticles	Moderate temperatures (300–700 °C), pH control during precipitation
Hydrothermal Synthesis	Reacting metal precursors in a sealed vessel at high pressure and temperature.	Controlled particle size, high crystallinity	High pressures (autoclave), moderate to high temperatures (150–300 °C)
Microwave-Assisted Synthesis	Using microwave radiation to heat precursors rapidly, leading to faster reaction times.	Fast processing, energy efficient, fine particles	Rapid heating, moderate to high temperatures (100–200 °C)
Mechanical Milling	Ball milling metal oxides or carbonates to achieve fine particle sizes before sintering.	Simple, scalable, cost-effective	Room temperature for milling, high temperatures for sintering
Spray Pyrolysis	Spraying a solution of metal salts into a hot furnace to form fine particles through pyrolysis.	Fine, spherical particles, continuous process	High temperatures (800–1200 °C), controlled spray conditions
Combustion Synthesis	Using a fuel and oxidizer mixture to ignite a self-sustaining combustion reaction.	Rapid, energy efficient, can produce high-purity products	Exothermic reaction, moderate temperatures (300–600 °C)
Chemical Vapor Deposition (CVD)	Decomposing metal precursors in vapor phase onto a substrate to form ferrites.	High purity, controlled composition, and thickness	High temperatures (500–1000 °C), vacuum or controlled atmosphere
Electrochemical Deposition	Electroplating metal ions onto a substrate to form ferrite films.	Precise thickness control, suitable for thin films	Room to moderate temperatures (25–100 °C), controlled current/voltage

Table 1 depicts different synthesis methods, description of techniques, key features of synthesis methods and requirement of typical conditions for synthesis of ferrites [17,24]. The synthesis of ferrites is critically important because it dictates the material's final properties, and including yield which can improve by optimizing key factors such as temperature, reaction time, pH level, precursor concentration, and stirring speed. Considering choice of the solvent and fuel to oxidant ratio in methods like sol-gel or auto-combustion plays a significant role, controlling reaction cooling

rates enhance product quality and yield, sometime crucial for their performance in various applications. By choosing and optimizing the synthesis method, researchers and engineers can tailor ferrites for specific uses, ensuring they meet the necessary requirements in fields ranging from electronics to medicine.

3. Biomedical applications of ferrites

Nanoferrites have obtained a significant attention due to their applications in different fields ranging from industry to biomedicine (**Figure 2**) [25]. One of the applications is magnetic resonance imaging (MRI), the most common use of nanoferrites in biomedicine field as a contrast agent. This MRI is a non-invasive diagnostic technique that helps to get detailed picture of the body tissues. MRI modifying the relaxation duration (T_1 and T_2) by adjacent water protons, iron oxides like magnetite helps find the difference between normal and diseased tissue by making the tissues harboring these nanoparticles seem brighter or darker in the MRI images. Similarly, manganese ferrite ($MnFe_2O_4$) and cobalt ferrite ($CoFe_2O_4$) used to get sharper, higher-resolution pictures [23–29]. The magnetic hyperthermia is a method where nanoferrites also used to treat cancer, magnetic nanoparticles are subjected to an alternating magnetic field, this technique utilized the particle's temperature. This heated particle injected in to the diseased tissues causes the tumor cells to heat up to a point where all cancer cells die, but leaving the surrounding healthy tissues unaffected [30–33]. Cobalt ferrites is a an important to treat the magnetic hypothermia-based cancer treatment using Cobalt ferrites which is a magnetic hyperthermia-based cancer therapy because of their high coercivity and magnetic saturation [34–36]. For magnetic refrigeration, key parameters include high magnetic anisotropy (K : 104 to 106 J/m³), significant adiabatic temperature change (ΔT_{ad} : 2–4 K at 2–5 Tesla), and a transition temperature near room temperature (T_c : 290–310K). Common materials include gadolinium (Gd), with a transition temperature of 293 K and ΔT_{ad} of ~3–4 K, and Gd-alloys like Gd-Si-Ge, which enhance refrigeration properties [37]. The main reason to study for the targeted drug delivery methods represents a notable's applications in biomedicine. Delivering medicines to targeted locations like tumor or particular organ these systems are intended to increase the effectiveness of medicine while lowering the amount of the drug that comes into contact with healthy tissues, to avoid adverse effects. The infected cells or organ medication is delivered in a regulated manner once it reaches the target, guaranteeing minimum systemic toxicity and high therapeutic concentrations at the illness site. Once the targeted organ treated very well need to make sure the health of the cells needs to monitor with the help of biosensors which is based on nano-ferrites which is also became very essential tool in diagnostics and healthcare. These biosensors designed to detect biological entities such as proteins, DNA, or pathogens. The combination of nano-ferrites with bio-molecules that bind to specific target analytes, these particles can provide highly sensitive detection of disease markers, toxins, or infectious agents. For example: Cobalt ferrite ($CoFe_2O_4$) and zinc ferrite ($ZnFe_2O_4$) ferrites used in biosensors due to their stability and large surface area, which improves ability of sensors and also its very important to detect early diagnosis, enabling more timely treatment and patient outcomes [36,37].The

nanoferrites can also exhibit strong antimicrobial properties that makes suitable for many applications in health care segment where infection control is critical, some nanoferrites, particularly those doped with other metals like zinc, copper and silver are known as disrupt the cell membranes of bacteria and fungi, leading to their destruction. This quality used in antimicrobial ferrites can be incorporated into medical device coatings, wound dressings, or even hospital textiles, where they act as barriers to microbial growth. This kind of feature is very important to prevent hospital acquired infections, which are major cause of complications and healthcare system [38–48]. In addition to this nano-ferrites are being explored for different use in this section medical field being explored for use in tissue engineering and regenerative medicine. When combined with biodegradable scaffolds, magnetic nanoparticles can be used to guide cell growth and tissue regranulation scaffolds, magnetic nanoparticles can be used to guide cell growth and tissue regeneration through the application of magnetic fields. This approach has been particularly promising in regeneration of bones and nerves, where magnetic fields can help to align bio cells in a way that mimics tissue natural growth, accelerating the healing process. Ferrites, NdFeB magnets, and Samarium Cobalt (SmCo) magnets exhibit distinct magnetic properties, making them suitable for various applications. Ferrites typically have a coercivity (H_c) ranging from 400 to 450 kA/m, a Curie temperature (T_c) between 300 and 450 °C, and an energy product (B_{Hmax}) of 1 to 5 MGOe (8 to 40 kJ/m³). In contrast, NdFeB magnets possess higher coercivity values, ranging from 800 to 2000 kA/m, with a Curie temperature of 310 to 400°C (which can be elevated with doping), and an impressive energy product of 30 to 55 MGOe (240 to 440 kJ/m³). Samarium Cobalt magnets also demonstrate significant coercivity, ranging from 600 to 2000 kA/m, with a higher Curie temperature of 720 to 820 °C and an energy product between 16 to 30 MGOe (128 to 240 kJ/m³) [23,49–54].




Figure 2. Schematic diagram of biological applications of ferrites.

3.1. Diagnosis and MRI imaging

Medical imaging being used an important tool by using ferrite nanoparticles which is very actively and effective in diagnosing cancer. Actually, these nanoparticles are very useful and have protentional to high to provide high quality

interior picture of human body. Magnetic Resonance Imaging (MRI) is the most widely used therapeutic instruments [55,57]. Diagnosing cancer or ill cell is not only that much important but finding exact locations, dimensions and distinction from healthy tissues. Nano ferrites such as CoFe_2O_4 and FeGa_2O_4 also one of the best examples for diagnostic applications because of their advantageous qualities, such as magnetic features that make them appropriate for improving contrast in MRI scans. Fe_3O_4 and $\gamma\text{-Fe}_2\text{O}_3$ Iron oxides nano-particles is studied for long time and being used as contrasting agents, beyond these improved imaging capabilities, manganese and Zinc doped zinc ferrite nano-particles, as well as $\text{Mn-ZnFe}_2\text{O}_4$ are also emerging as viable possibilities [41,50].

MnFe_2O_4 ferrites are the nano particles are new MRI contrast agents that provide better performance than conventional ferrites like Fe_3O_4 , $\gamma\text{-Fe}_2\text{O}_3$, CoFe_2O_4 , and NiFe_2O_4 best for magnetic characteristics including their reduced toxicity and biocompatibility. Using MnFe_2O_4 nano-particles in MRI and developing new ferrites nanoparticles to open new possibilities for better early diagnosis and management of a range of illnesses [35,41].

3.2. Hyperthermia

Magnetic hyperthermia is important and cutting-edge technical tool to cure cancer, in this method heat applies to tumor location in order to kill cancerous cells. The process of heating at exact location is possible by only using ferrite-based nanoparticles have a special capacity to absorb energy when exposed to an external alternating magnetic field [32,34,35]. The successful elimination of malignant cells while protecting healthy ones, a condition known as hyperthermia [54,55]. This treatment technique is very sensitive technique to eliminate malignancy at exact location resulting in classifications of localized, regional, whole-body hyperthermia [54]. Tumor cells are intrinsically more heat-sensitive than normal cells because of their atypical blood arteries, these arteries work differently so this is very weak and more sensitive towards heat. The Fe_3O_4 applied for tumor treatment are proficiently studied, these nanoparticles use Néel and Brownian relaxation to collect energy from the magnetic field and transform it into heat [55]. CoFe_2O_4 nanoferrite has immense capacity of self-heating and therefore is the most encouraging nanoferrite for application of hyperthermia [57]. These nanoparticles magnetic nature, size and shape of a particle, including intensity and frequency of the applied magnetic field, all these depends on how much heat they produce. The Fe_2O_4 nanoferrite or CoFe_3O_4 are able to absorb magnetic energy and releasing it as heat (42–45 °C) due to this is used in hyperthermia treatments. This type of treatment helps to kill directly or make very weak towards the treatment like radiation and chemotherapy. This technological development provides focused, non-invasive approach to cancer treatment which has great potential to improve the efficacy of currently available medicines and lessons the adverse effects of old traditional approaches.

3.3. Drug delivery and release

Ferrite nanoparticles show significant advantages such as treating cancer, delivery of drug and its release and safe excretion from the human body. For instance,

the test carried on synthesized CoFe_2O_4 nanoparticles disclosed all the above-mentioned benefits [58]. In comparison with conventional drug use, the utilization of nanoferrites has helped to minimize the requirement of drug needed and related side effects [59,60]. In treating cancer by this system, the nanoferrites act as core whereas various biocompatible organic moieties act as shell. Ferrite nanoparticles are capable of carrying drugs and circulating them without dripping. They also effortlessly travel to the site of target tumor with the help of an external magnetic field. They support in lending effective treatment by bypassing normal cells [61]. After delivering the drugs, either they get removed from the human body or get biodegradable [62]. The method of targeted drug delivery is having various benefit's like depletion of wastage of drug, minimizing the drug administration frequency, lowering side-effects, increasing efficacy of treatment, being safe and reliable [32] etc. manganese (II) complexes is a high catalytic activity which has a potential benefit in medical applications, for drug synthesis or therapeutic applications which is helpful medication manufacturing and treatment procedures [63]. Zirconium oxide (ZrO_2) synthesized material which has high optical characteristics and cubic structure with size of the grain ZrO_2 is 10–30 nm due to this which suitable to get improved by surfactants like polyethylene glycol (PEG) have great potential which is used for drug delivery [64]. Copper (II) hexaaza macrocyclic complexes is new content which is synthesized by using situ one-pot template synthesis (IOPTS) ultimately a good for drug delivery [65]. Ferrites are valuable in various applications, including drug delivery, antibacterial/antifungal treatments, and water treatment, due to their unique properties. For drug delivery, key parameters such as particle size (10–100 nm), magnetic saturation (50–80 emu/g), biocompatibility (surface-coated with PEG, silica, dextran), and zeta potential (–30 to +30 mV) enhance cellular uptake and ensure effective targeting and stability. In antibacterial and antifungal applications, small particle size (10–50 nm), appropriate magnetic saturation (40–70 emu/g), surface functionalization with antimicrobial agents, and chemical stability in various environments are crucial for maximizing antimicrobial efficacy. For water treatment, ferrites should exhibit a particle size of 10–200 nm, magnetic saturation of 50–70 emu/g, high chemical stability across pH ranges, and a large surface area (50–150 m^2/g) to optimize pollutant removal and ensure durability in treatment processes [54,66–68].

3.4. Antibacterial and antifungal studies

Nano ferrites exhibit antibacterial and antifungal properties due to several key factors related to their unique chemical composition, surface characteristics, and magnetic properties. Nano ferrites possess a high surface-to-volume ratio, which increases the interaction between the nanoparticles and microbial cells. This enhanced contact can lead to more efficient microbial killing. The surface of nano ferrites can generate reactive oxygen species (ROS) when exposed to environmental conditions. ROS, such as hydroxyl radicals, superoxide anions, and hydrogen peroxide, can damage microbial cell membranes, proteins, and DNA, leading to cell death. Magnetic nanoparticles are significantly used as antibacterial and antifungals. The preparation and verification are done for nanoferrites for their extensive usage in

medicinal field [69,70]. As antifungals are toxic, less efficient and resistant, there is a need for developing novel antifungal drugs that are safe and efficient. Therefore, taking into account these aspects, new antifungal substances have evolved [71]. Cobalt ferrite nanoparticles have been shown to exhibit significant antibacterial activity. The mechanism involves the generation of ROS and the release of cobalt ions, which can penetrate bacterial cells and cause oxidative damage. Zinc ferrite nanoparticles are known for their antifungal activity. Zinc ions can interfere with fungal cell wall synthesis and membrane integrity, while the ferrite structure helps in the generation of ROS, leading to fungal cell death. Thus Nano ferrites show antibacterial and antifungal properties due to their high surface area, magnetic properties, metal ion release, and ability to generate reactive oxygen species. These properties make them effective in disrupting microbial cells and killing bacteria and fungi.

The Kirby–Bauer also called agar diffusion test is an antibiotic susceptibility test that makes use of discs of antibiotics to examine the extent of bacteria and fungi [72]. Zinc Copper ferrites were studied for antibacterial activity where it was noticed that activity was dependent of zinc concentration [53]. The Zinc substituted Cobalt ferrite and Manganese substituted Cobalt ferrite were utilized for antibacterial and antibiofilm activities towards bacteria that commonly diffused on the surfaces of medical operating room walls [73]. The Mg substituted Mn-Zn ferrites act as outstanding antimicrobial potentials [42].

Also, the cobalt doped manganese ferrites are proposed as a candidate material for industries manufacturing antifungal products [74]. Ag doped Ni Co nanoferrites show an exceptional antifungal action [75]. **Figure 3** is a schematic representation of biological applications of ferrites whereas **Table 2** provides information about different biological applications of ferrites along with the description. Thenanoferrite sample $\text{Ni}_{0.45}\text{Zn}_{0.45}\text{Cu}_{0.1}\text{Fe}_2\text{O}_4$ exhibited the highest antibacterial activity against *Bacillus cereus*, with inhibition zones measuring 21, 23, 23, and 23 mm for concentrations of 25, 50, 100, and 250 $\mu\text{g}/\text{ml}$, respectively (**Table 3**). **Figure 4** and **Figure 5** illustrate the antibacterial studies of nickel zinc ferrites and copper-doped nickel zinc ferrites. In contrast, the other nanoferrite samples demonstrated negligible antibacterial activity. The antifungal activity was evaluated for cobalt-doped nickel zinc ferrites, with $\text{Ni}_{0.45}\text{Zn}_{0.35}\text{Co}_{0.2}\text{Fe}_2\text{O}_4$ showing the highest inhibition zones of 25, 27, 30, and 30 mm for 25, 50, 100, and 250 $\mu\text{g}/\text{ml}$ concentrations against *Aspergillus niger* (**Table 4**) [56]. **Figures 6** and **7** present the antifungal studies of nickel zinc ferrites and cobalt-doped nickel zinc ferrites. The results highlight the importance of compositional variations in enhancing the antimicrobial properties of nanoferrites, paving the way for their potential use in biomedical applications.

Table 2. Biological applications of ferrites with description.

Biological application	Description	Reference
MRI Contrast Agents	Ferrite nanoparticles enhance MRI contrast by affecting the relaxation times of hydrogen nuclei in tissues.	71
Drug Delivery	Magnetic ferrite nanoparticles can be directed to specific locations in the body using an external magnetic field, allowing for controlled drug release.	72
Hyperthermia Treatment	Magnetic ferrite nanoparticles generate heat when exposed to an alternating magnetic field, which can be used to kill cancer cells selectively.	73
Biosensors	Ferrite nanoparticles enhance the sensitivity and specificity of biosensors used to detect various biological molecules.	38
Cell Separation	Cells can be tagged with magnetic ferrite nanoparticles and separated from a mixture using a magnetic field.	74
Antifungal Applications	Ferrite nanoparticles exhibit antifungal properties, inhibiting the growth of various fungal species.	42
Antimicrobial Applications	Ferrite nanoparticles have antimicrobial properties effective against a wide range of bacterial strains.	43
Antibacterial Coatings	Ferrite nanoparticles can be used in coatings to prevent bacterial colonization on medical devices.	44
Antimicrobial Textiles	Ferrite nanoparticles are incorporated into textiles to provide long-lasting antimicrobial properties.	45
Water Purification	Ferrite nanoparticles can be used to remove microbial contaminants from water, providing an effective purification method.	46




Figure 3. Schematic diagram of biological applications of ferrites.

Table 3. Antibacterial activity of copper doped nickel zinc nano ferrites against bacillus cerus.

Sample	Zone of inhibition(mm)			
	25µg/mL	50µg/mL	100 µg/mL	250 µg/mL
Ni _{0.45} Zn _{0.55} Fe ₂ O ₄	1	1	2	1
Ni _{0.45} Zn _{0.45} Cu _{0.1} Fe ₂ O ₄	21	23	23	23
Ni _{0.45} Zn _{0.35} Cu _{0.2} Fe ₂ O ₄	1	1	2	1
Ni _{0.45} Zn _{0.25} Cu _{0.3} Fe ₂ O ₄	1	1	2	1




Figure 4. Antibacterial activity of nickel zinc nanoferrites ($\text{Ni}_{0.45}\text{Zn}_{0.55}\text{Fe}_2\text{O}_4$) against *Bacillus cereus*.




Figure 5. Antibacterial activity of copper doped nickel zinc nanoferrites ($\text{Ni}_{0.45}\text{Zn}_{0.45}\text{Cu}_{0.1}\text{Fe}_2\text{O}_4$) against *Bacillus cereus*.

Table 4. Antifungal activity of cobalt doped nickel zinc nanoferrites against *Aspergillus niger*.

Sample	Zone of inhibition(mm)			
	25µg/mL	50µg/mL	100 µg/mL	250 µg/mL
$\text{Ni}_{0.45}\text{Zn}_{0.55}\text{Fe}_2\text{O}_4$	1	2	2	1
$\text{Ni}_{0.45}\text{Zn}_{0.45}\text{Co}_{0.1}\text{Fe}_2\text{O}_4$	1	2	2	1
$\text{Ni}_{0.45}\text{Zn}_{0.35}\text{Co}_{0.2}\text{Fe}_2\text{O}_4$	25	27	30	30
$\text{Ni}_{0.45}\text{Zn}_{0.25}\text{Co}_{0.3}\text{Fe}_2\text{O}_4$	1	2	2	2




Figure 6. Antifungal activity of nickel zinc nanoferrites ($\text{Ni}_{0.45}\text{Zn}_{0.55}\text{Fe}_2\text{O}_4$) against *Aspergillus niger*.




Figure 7. Antifungal activity of cobalt doped nickel zinc nanoferrites ($\text{Ni}_{0.45}\text{Zn}_{0.35}\text{Co}_{0.2}\text{Fe}_2\text{O}_4$) against *Aspergillus niger*.

Thus unique magnetic properties and biocompatibility of ferrites (**Table 5**) make them invaluable in various biological and medical applications, shown in **Figure 8**. Research continues to expand their potential uses, offering promising advancements in diagnostics, treatment, and research methodologies in the life sciences. Ferrites exhibit notable antibacterial and antifungal properties, with particle sizes typically ranging from 10–50 nm for Fe_3O_4 (magnetite), effective against *E. coli* and *S. aureus*, and 20–60 nm for CoFe_2O_4 (cobalt ferrite), demonstrating antibacterial activity against *E. coli*. Their magnetic saturation (M_s) values are 40–60 emu/g for magnetite, enhancing drug targeting, and 25–35 emu/g for ZnFe_2O_4 (zinc ferrite), which still shows moderate antibacterial activity. Zeta potential for magnetite ranges from -10 to -20 mV, ensuring stability in colloidal suspension. Minimum inhibitory concentrations (MIC) for Fe_3O_4 nanoparticles are 50–100 $\mu\text{g/mL}$ for *E. coli* and *S. aureus*. CoFe_2O_4 achieves 80%–90% antibacterial efficiency against *E. coli*, while NiFe_2O_4 (nickel ferrite) shows 70%–85% antifungal efficiency against *C. albicans*. Functionalizing ferrites, such as with silver, further enhances antibacterial activity. Ferrites are biocompatible, with cytotoxicity showing $\geq 80\%$ cell viability at ≤ 100 $\mu\text{g/mL}$ [68,76–80].

Table 5. Applications, key parameters, and their importance.

Application	Important Parameters	Reasons for Importance
Microwave Frequency Devices	Permeability, Loss Tangent (High ($\mu > 1000$, Low ($\tan \delta < 0.1$))	High permeability ensures efficient signal transmission, while low loss tangents minimize energy loss.
	Frequency Response	Affects device performance at various microwave frequencies.
Computer Memory Core Elements	Magnetic Saturation (50–80 emu/g), Coercivity ($H_c \sim 20$ –300 Oe) ($H_c \sim 20$ –300 Oe) ($H_c \sim 20$ –300 Oe)	High saturation magnetization allows for reliable data storage and retrieval; moderate coercivity ensures stability.
	Thermal Stability	Essential for maintaining performance under operating conditions.
Biomedical Applications	Biocompatibility, Particle Size	Biocompatibility is crucial for safety; smaller particles enhance cellular uptake and interaction with tissues.
	Particle Size 10–100 nm	Enhances cellular uptake and improves interactions with biological systems.
	Surface Functionalization	Modifications improve interactions with biological systems, reducing toxicity.
Diagnosis	Magnetic Susceptibility, Surface Coating	High susceptibility enhances imaging quality; biocompatible coatings improve safety in medical applications.
	Sensitivity and Resolution	Crucial for improving diagnostic accuracy in imaging techniques.
Hyperthermia	Specific Absorption Rate	High SAR values indicate efficient heat generation, while smaller sizes improve localization in tumors.
	Particle Size (10–50 nm)	
Drug Delivery	Magnetic Properties	Essential for effective induction heating in targeted cancer therapy.
	Magnetic Saturation (Ms), Biocompatibility	Enables targeted delivery through external magnetic fields; biocompatibility ensures safety.
	Release Profile	Important for controlling drug release rates in therapeutic applications.
Antibacterial and Antifungal	Particle Size (10–50 nm)	Smaller sizes enhance interaction with microbes; functionalization improves antimicrobial efficacy.
	Surface Functionalization, Chemical Stability	
Water Treatment	Efficacy in Biological Environments	Chemical stability ensures prolonged activity in diverse conditions.
	Particle Size (10–200 nm)	
	Magnetic Saturation (Ms), (50–70 emu/g)	Nano-sized particles provide high surface area for adsorption; magnetic properties enable easy recovery.
	Surface Area (50–150 m ² /g)	
	Chemical Stability	Ensures durability and effectiveness during treatment processes across various pH levels.




Figure 8. Various biological applications of nano ferrites.

3.5. Waste water treatment

Water sources are at high risk of pollution. They get polluted because of discharging wastes into the water bodies such as plastic, glass, chemicals, etc. The common pollutants in waste water are metal ions, aromatic compounds, anions, phenols, dyes, pesticides, detergents, etc. Because of the presence of such contaminants in waste water, it makes the water unfit for drinking and also becomes poisonous to aquatic life. Ferrites, especially those with high surface areas, are effective adsorbents for removing heavy metals like lead (Pb^{2+}), cadmium (Cd^{2+}), chromium (Cr^{6+}), and arsenic (As^{3+}) from wastewater due to unique properties of ferrites (**Figure 9**). The metal ions are adsorbed onto the surface of the ferrite particles through electrostatic interactions and chemical bonding. Ferrites can adsorb organic pollutants, such as dyes, from wastewater due to their surface properties and ability to be modified with functional groups that enhance adsorption. All over the world, there is demand for clean and safe water. Hence, the purification of water is of utmost priority. New methods of purification of water are to be developed that are cost effective. Magnetic nanoparticles because of their adsorption and high surface area to volume ratio have become significant candidates for treating waste water. Therefore, nanoferrites are checked for removing contaminants and purifying water. They have proved to be promising candidates in this aspect. The process of adsorption or degradation is responsible for the removal of contaminants in water [47,81–84]. The waste water of the industries is treated to remove dyes and phenols, toxic metals by using nanoferrites [75–82]. Magnetite (Fe_3O_4), Cobalt Ferrite (CoFe_2O_4), Nickel Ferrite (NiFe_2O_4), Zinc Ferrite (ZnFe_2O_4), Copper Ferrite (CuFe_2O_4), Manganese Ferrite (MnFe_2O_4), and Barium Ferrite ($\text{BaFe}_{12}\text{O}_{19}$)—is used in wastewater treatment for specific applications based on their magnetic properties, ability to adsorb contaminants, and catalytic capabilities. Nanoferrites are good adsorbents that are of low cost, efficient, can be recovered with ease and reused. By literature review, it is clear that trend of using nanoferrites in waste water treatment has increased. The Fe_3O_4 is a popular candidate for this. This might be because of non-toxicity, ease of availability of precursors required in its synthesis [32,85]. $\text{Dy}_2\text{O}_3\text{-SiO}_2$ nanocomposite is best and effective in photocatalysis which break down the pollutants like erythrosine so it's best for sanitation and environmental cleanup similarly reduced graphene oxide (RGO) from graphite oxide using urea also used as non-toxic reducing agent. [70,86]. CsPbI_3 perovskite nanostructures is capable

enough fight against the *Pseudomonas aeruginosa*, *Escherichia coli*, and *Streptococcus pyogenes* which is good to addressing pollution [86]. Ferrites with a large surface area (50–150 m²/g) demonstrate high adsorption capacities, making them effective for removing heavy metals and dyes in water treatment applications. Their high magnetic saturation (Ms) values, particularly in magnetite (50–60 emu/g), facilitate easy magnetic separation, which is beneficial for magnetic filtration systems. The adsorption capacity of ferrites is quantified in mg of pollutant per gram of ferrite, with magnetite nanoparticles exhibiting significant adsorption capabilities for heavy metals like Pb²⁺, Cr⁶⁺, and As³⁺. Ferrites also show remarkable removal efficiencies, achieving 90%–95% removal rates for pollutants such as Pb²⁺, As³⁺, and Cr⁶⁺. Additionally, ferrites like Fe₃O₄ maintain good stability across a wide pH range (4–9), enhancing their versatility for various wastewater treatment scenarios. Some ferrites, such as NiFe₂O₄, possess antimicrobial properties, allowing them to function as disinfectants in water treatment systems. [36,66,87–90]



Figure 9. Advantages of nano ferrites in using them for waste and waste water treatment as compared to conventional techniques.

4. Conclusions

In conclusion, ferrite synthesis techniques are essential for determining their magnetic, chemical, and physical characteristics; all synthesis techniques are widely and effectively synthesized and utilized. Sol-gel, co-precipitation, hydrothermal, and green synthesis methods are used to get the desired particle size, shape, and magnetic properties, depending on the application synthesis method utilized. Using the best synthesis method, prepared ferrites provide flexibility in health care, demonstrated by their biomedical applications, mainly in medication administration, magnetic hyperthermia, biosensing, and magnetic resonance imaging (MRI). CoFe₃O₄ and MnFe₃O₄ are essential for MRI to get strong magnetic characteristics and biocompatibility, which helps MRI to contrast agents and cancer therapies. Various methods of synthesis of ferrites are discussed to get information related to antimicrobial properties and biological applications of ferrites, such as the biomedical field comprising cancer diagnosis, MRI, hyperthermia, drug delivery and release, antimicrobial properties, and wastewater treatment.

Compared with conventional drug use, the utilization of nano-ferrites has helped minimize the amount of drug needed and avoid side effects. In wastewater treatment, nano-ferrites are cost-effective and efficient compared to conventional methods. Also, nano-ferrites are promising candidates for antimicrobial and biomedical applications. The optimization of feature synthesis techniques is

necessary to improve the biocompatibility, stability, and magnetic properties of ferrites for specific biomedical applications by considering green synthesis methods to avoid or minimize environmental impact while maintaining the exact cost-effectiveness and efficacy in applications such as wastewater treatment, drug delivery, and hyperthermia. Multifunctional ferrites are most important and have a high potential for new avenues in fields like theragnostic, fusing their medicinal and diagnostic properties and increasing their application in environmental sustainability and antimicrobial treatments.

Conflict of interest: The authors declare no conflict of interest.

References

1. Buschow KHJ, de Boer FR. *Physics of Magnetism and Magnetic Materials*. Springer US; 2003.
2. Broese van Groenou A, Bongers PF, Stuys AL. Magnetism, microstructure and crystal chemistry of spinel ferrites. *Materials Science and Engineering*. 1969; 3(6): 317-392. doi: 10.1016/0025-5416(69)90042-1
3. Gupta M. Synthesis of nanosized ferrites by solution combustion method and investigation on their magnetic and electrical properties. Available online: <http://hdl.handle.net/10603/10671> (accessed on 22 September 2024).
4. Leslie-Pelecky DL, Rieke RD. Magnetic Properties of Nanostructured Materials. *Chemistry of Materials*. 1996; 8(8): 1770-1783. doi: 10.1021/cm960077f
5. Chee KL, Yong SK, No YP, et al. Multibit MRAM using a pair of memory cells. *IEEE Transactions on Magnetics*. 2005; 41(10): 2670-2672. doi: 10.1109/tmag.2005.855288
6. Jadhav P, Patankar K, Mathe V, et al. Structural and magnetic properties of $\text{Ni}_{0.8}\text{Co}_{0.2-2x}\text{Cu}_x\text{Mn}_x\text{Fe}_2\text{O}_4$ spinel ferrites prepared via solution combustion route. *Journal of Magnetism and Magnetic Materials*. 2015; 385: 160-165. doi: 10.1016/j.jmmm.2015.03.020
7. Sugimoto M. The Past, Present, and Future of Ferrites. *Journal of the American Ceramic Society*. 1999; 82(2): 269-280. doi: 10.1111/j.1551-2916.1999.tb20058.x
8. Shaikh PA, Kambale RC, Rao AV, et al. Structural, magnetic and electrical properties of Co–Ni–Mn ferrites synthesized by co-precipitation method. *Journal of Alloys and Compounds*. 2010; 492(1-2): 590-596. doi: 10.1016/j.jallcom.2009.11.189
9. Anis-ur-Rehman M, Malik MA, Akram M, et al. Proficient magnesium nanoferrites: synthesis and characterization. *Physica Scripta*. 2011; 83(1): 015602. doi: 10.1088/0031-8949/83/01/015602
10. Amiri M, Salavati-Niasari M, Akbari A. Magnetic nanocarriers: Evolution of spinel ferrites for medical applications. *Advances in Colloid and Interface Science*. 2019; 265: 29-44. doi: 10.1016/j.cis.2019.01.003
11. Rana G, Dhiman P, Kumar A, et al. Recent advances on nickel nano-ferrite: A review on processing techniques, properties and diverse applications. *Chemical Engineering Research and Design*. 2021; 175: 182-208. doi: 10.1016/j.cherd.2021.08.040
12. Joshi S, Kumar M, Chhoker S, et al. Structural, magnetic, dielectric and optical properties of nickel ferrite nanoparticles synthesized by co-precipitation method. *Journal of Molecular Structure*. 2014; 1076: 55-62. doi: 10.1016/j.molstruc.2014.07.048
13. Roca AG, Costo R, Rebolledo AF, et al. Progress in the preparation of magnetic nanoparticles for applications in biomedicine. *Journal of Physics D: Applied Physics*. 2009; 42(22): 224002. doi: 10.1088/0022-3727/42/22/224002
14. Ghosh N, Pant P, Bhuvaneshwari S. Chemical Methodologies for Preparation of Micron and Nanometer Scale Ferrites-A Mini Review of Patents. *Recent Patents on Nanotechnology*. 2008; 2(1): 8-18. doi: 10.2174/187221008783478653
15. Landrum GA, Genin H. Application of machine-learning methods to solid-state chemistry: ferromagnetism in transition metal alloys. *J Solid State Chem*. 2003; 176(2): 587-593. doi: 10.1016/S0022-4596(03)00343-8
16. Byrappa K, Adschiri T. Hydrothermal technology for nanotechnology. *Progress in Crystal Growth and Characterization of Materials*. 2007; 53(2): 117-166. doi: 10.1016/j.pcrysgrow.2007.04.001
17. Sushant S.K, Choudhari N.J, Patil S, et al. Development of M–NiFe₂O₄ (Co, Mg, Cu, Zn, and Rare Earth Materials) and the Recent Major Applications. *International Journal of Self-Propagating High-Temperature Synthesis*. 2023; 32(2): 61-116. doi: 10.3103/s1061386223020061

18. Pulišová P, Kováč J, Voigt A, et al. Structure and magnetic properties of Co and Ni nano-ferrites prepared by a two step direct microemulsions synthesis. *Journal of Magnetism and Magnetic Materials*. 2013; 341: 93-99. doi: 10.1016/j.jmmm.2013.04.003
19. Uzo Anya A, and HMusa S. A Review of Processes Used in Polyol Synthesis from Vegetable Oils. *Scholars Academic Journal of Biosciences (SAJB)*. 2024; 2(2): 141-143.
20. Afgan NH, Al Gobaisi D.A, Carvalho M.G, and Cumo M. Sustainable energy development. *Renewable and Sustainable Energy Reviews*. 1998; 2(3): 235-286. doi: 10.1016/S1364-0321(98)00002-1
21. Yue Z, Li L, Zhou J, et al. Preparation and characterization of NiCuZn ferrite nanocrystalline powders by auto-combustion of nitrate-citrate gels. *Materials Science and Engineering: B*. 1999; 64(1): 68-72. doi: 10.1016/S0921-5107(99)00152-X
22. Pramanik P. Novel chemical route for the preparation of nanosized oxides, phosphates, vanadates, molybdates and tungstates using polymer precursors. *Bulletin of Materials Science* 1999; 22(3): 335-339. doi: 10.1007/BF02749940/METRICS
23. Shweta GM, Naik LR, Pujar RB, et al. Influence of magnesium doping on structural and elastic parameters of Nickel Zinc nanoferrites. *Materials Chemistry and Physics*. 2021; 257: 123825. doi: 10.1016/j.matchemphys.2020.123825
24. Kaziet S. Sintering Temperature Dependent Structural and Mechanical Studies of $BaxPb1 - xTiO3$ Ferroelectrics. *Journal of Nano- and Electronic Physics*. 2020; 12(4): 4018. doi: 10.21272/JNEP.12(4).04018
25. Shweta GM, Naik LR, Pujar RB, and Mathad SN. Copper-Doped Nickel Zinc Nano-ferrites by Solution-Combustion Synthesis Using Sucrose as a Fuel. *International Journal of Self-Propagating High-Temperature Synthesis*. 2020; 29(4): 208-212. doi: 10.3103/S1061386220040135/TABLES/3
26. Mahfouz MG, Galhoum AA, Gomaa NA, et al. Uranium extraction using magnetic nano-based particles of diethylenetriamine-functionalized chitosan: Equilibrium and kinetic studies. *Chemical Engineering Journal*. 2015; 262: 198-209. doi: 10.1016/j.cej.2014.09.061
27. Flores RG, Andersen SLF, Maia LKK, et al. Recovery of iron oxides from acid mine drainage and their application as adsorbent or catalyst. *Journal of Environmental Management*. 2012; 111: 53-60. doi: 10.1016/j.jenvman.2012.06.017
28. Hasanzadeh M, Shadjou N, de la Guardia M. Iron and iron-oxide magnetic nanoparticles as signal-amplification elements in electrochemical biosensing. *TrAC Trends in Analytical Chemistry*. 2015; 72: 1-9. doi: 10.1016/j.trac.2015.03.016
29. Qu X, Alvarez PJJ, Li Q. Applications of nanotechnology in water and wastewater treatment. *Water Research*. 2013; 47(12): 3931-3946. doi: 10.1016/j.watres.2012.09.058
30. Plouffe BD, Murthy SK, Lewis LH. Fundamentals and application of magnetic particles in cell isolation and enrichment: a review. *Reports on Progress in Physics*. 2014; 78(1): 016601. doi: 10.1088/0034-4885/78/1/016601
31. Yang M, Gao L, Liu K, et al. Characterization of $Fe_3O_4/SiO_2/Gd_2O(CO_3)_2$ core/shell/shell nanoparticles as T1 and T2 dual mode MRI contrast agent. *Talanta*. 2015; 131: 661-665. doi: 10.1016/j.talanta.2014.08.042
32. Kefeni KK, Mamba BB, Msagati TAM. Application of spinel ferrite nanoparticles in water and wastewater treatment: A review. *Separation and Purification Technology*. 2017; 188: 399-422. doi: 10.1016/j.seppur.2017.07.015
33. Kim DH, Nikles DE, Brazel CS. Synthesis and Characterization of Multifunctional Chitosan- $MnFe_2O_4$ Nanoparticles for Magnetic Hyperthermia and Drug Delivery. *Materials*. 2010; 3(7): 4051-4065. doi: 10.3390/ma3074051
34. Kumar CSSR, Mohammad F. Magnetic nanomaterials for hyperthermia-based therapy and controlled drug delivery. *Advanced Drug Delivery Reviews*. 2011; 63(9): 789-808. doi: 10.1016/j.addr.2011.03.008
35. Peiravi M, Eslami H, Ansari M, et al. Magnetic hyperthermia: Potentials and limitations. *Journal of the Indian Chemical Society*. 2022; 99(1): 100269. doi: 10.1016/j.jics.2021.100269
36. Wang J. Electrochemical biosensors: Towards point-of-care cancer diagnostics. *Biosensors and Bioelectronics*. 2006; 21(10): 1887-1892. doi: 10.1016/j.bios.2005.10.027
37. Brück E, Tegus O, Cam Thanh DT, et al. A review on Mn based materials for magnetic refrigeration: Structure and properties. *International Journal of Refrigeration*. 2008; 31(5): 763-770. doi: 10.1016/j.ijrefrig.2007.11.013
38. Sun C, Lee JSH, Zhang M. Magnetic nanoparticles in MR imaging and drug delivery. *Advanced Drug Delivery Reviews*. 2008; 60(11): 1252-1265. doi: 10.1016/j.addr.2008.03.018
39. Karimi Z, Karimi L, Shokrollahi H. Nano-magnetic particles used in biomedicine: Core and coating materials. *Materials Science and Engineering: C*. 2013; 33(5): 2465-2475. doi: 10.1016/j.msec.2013.01.045
40. Abdel Maksoud MIA, El-Sayyad GS, El-Khawaga AM, et al. Nanostructured Mg substituted Mn-Zn ferrites: A magnetic recyclable catalyst for outstanding photocatalytic and antimicrobial potentials. *Journal of Hazardous Materials*. 2020; 399: 123000. doi: 10.1016/j.jhazmat.2020.123000

41. Mahamuni-Badiger P, Ghare V, Nikam C, et al. The fungal infections and their inhibition by Zinc oxide nanoparticles: an alternative approach to encounter drug resistance. *The Nucleus*. 2023; 67(2): 291-309. doi: 10.1007/s13237-023-00439-1
42. Arakha M, Pal S, Samantarrai D, et al. Antimicrobial activity of iron oxide nanoparticle upon modulation of nanoparticle-bacteria interface. *Scientific Reports*. 2015; 5(1). doi: 10.1038/srep14813
43. Mahdavi M, Namvar F, Ahmad M, et al. Green Biosynthesis and Characterization of Magnetic Iron Oxide (Fe₃O₄) Nanoparticles Using Sea-weed (*Sargassum muticum*) Aqueous Extract. *Molecules*. 2013; 18(5): 5954-5964. doi: 10.3390/molecules18055954
44. Kalia R, Verma R, Chauhan A, Sharma A, Kumar R. Recent Advances and Trends in ZnO Hybrid Nanostructures. *ZnO and Their Hybrid Nano-Structures: Potential Candidates for Diverse Applications*.
45. Ahmed S, Ahmad M, Swami BL, et al. A review on plants extract mediated synthesis of silver nanoparticles for antimicrobial applications: A green expertise. *Journal of Advanced Research*. 2016; 7(1): 17-28. doi: 10.1016/j.jare.2015.02.007
46. Muhamad Arshad J, Raza W, Amin N, et al. Synthesis and characterization of cobalt ferrites as MRI contrast agent. *Materials Today: Proceedings*. 2021; 47: S50-S54. doi: 10.1016/j.matpr.2020.04.746
47. Yang H, Zhang C, Shi X, et al. Water-soluble superparamagnetic manganese ferrite nanoparticles for magnetic resonance imaging. *Biomaterials*. 2010; 31(13): 3667-3673. doi: 10.1016/j.biomaterials.2010.01.055
48. Nasrin S, Chowdhury, Moazzam Hossen M, et al. Study of the suitability of manganese-substituted cobalt ferrites nanoparticles as MRI contrast agent and treatment by employing hyperthermia temperature. *Journal of Magnetism and Magnetic Materials*. 2022; 564: 170065. doi: 10.1016/j.jmmm.2022.170065
49. Umut E, Coşkun M, Pineider F, et al. Nickel ferrite nanoparticles for simultaneous use in magnetic resonance imaging and magnetic fluid hyperthermia. *Journal of Colloid and Interface Science*. 2019; 550: 199-209. doi: 10.1016/j.jcis.2019.04.092
50. Maksoud MIAA, El-Sayyad GS, Ashour AH, et al. Antibacterial, antibiofilm, and photocatalytic activities of metals-substituted spinel cobalt ferrite nanoparticles. *Microbial Pathogenesis*. 2019; 127: 144-158. doi: 10.1016/j.micpath.2018.11.045
51. Camacho-González MA, Quezada-Cruz M, Cerón-Montes GI, et al. Synthesis and characterization of magnetic zinc-copper ferrites: Antibacterial activity, photodegradation study and heavy metals removal evaluation. *Materials Chemistry and Physics*. 2019; 236: 121808. doi: 10.1016/j.matchemphys.2019.121808
52. Naik AB, Naik PP, Hasolkar SS, et al. Structural, magnetic and electrical properties along with antifungal activity & adsorption ability of cobalt doped manganese ferrite nanoparticles synthesized using combustion route. *Ceramics International*. 2020; 46(13): 21046-21055. doi: 10.1016/j.ceramint.2020.05.177
53. Dhanda N, Thakur P, Aidan Sun AC, et al. Structural, optical and magnetic properties along with antifungal activity of Ag-doped Ni-Co nanoferrites synthesized by eco-friendly route. *Journal of Magnetism and Magnetic Materials*. 2023; 572: 170598. doi: 10.1016/j.jmmm.2023.170598
54. Laurent S, Dutz S, Häfeli UO, et al. Magnetic fluid hyperthermia: Focus on superparamagnetic iron oxide nanoparticles. *Advances in Colloid and Interface Science*. 2011; 166(1-2): 8-23. doi: 10.1016/j.cis.2011.04.003
55. Khosroshahi ME, Ghazanfari L, Hasan-Nejad Z. Preliminary Results of Treating Cancerous Cells of Lung (QU-DB) by Hyperthermia using Diode Laser and Gold Coated Fe₃O₄ /SiO₂ Nano-Shells: An in-Vitro Assay. *Iranian Journal of Medical Physics*. 2012; 9(4): 254.
56. Tran N, Webster TJ. Magnetic Nano-Particles: Biomedical Applications And Challenges. *Journal of Materials Chemistry*. 2010; 20(40): 8760. doi: 10.1039/c0jm00994f
57. Lee S.W, Bae S, Takemura Y, et al. Self-heating characteristics of cobalt ferrite nanoparticles for hyperthermia application. *Journal of Magnetism and Magnetic Materials*. 2007; 310(2): 2868-2870. doi: 10.1016/j.jmmm.2006.11.080
58. Dey C, Baishya K, Ghosh A, et al. Improvement of drug delivery by hyperthermia treatment using magnetic cubic cobalt ferrite nanoparticles. *Journal of Magnetism and Magnetic Materials*. 2017; 427: 168-174. doi: 10.1016/j.jmmm.2016.11.024
59. Valente F, Astolfi L, Simoni E, et al. Nanoparticle drug delivery systems for inner ear therapy: An overview. *Journal of Drug Delivery Science and Technology*. 2017; 39: 28-35. doi: 10.1016/j.jddst.2017.03.003
60. Yu X, Zhu Y. Preparation of magnetic mesoporous silica nanoparticles as a multifunctional platform for potential drug delivery and hyperthermia. *Science and Technology of Advanced Materials*. 2016; 17(1): 229-238. doi: 10.1080/14686996.2016.1178055
61. Bahrami B, Hojjat-Farsangi M, Mohammadi H, et al. Nanoparticles and targeted drug delivery in cancer therapy. *Immunology Letters*. 2017; 190: 64-83. doi: 10.1016/j.imlet.2017.07.015

62. Krishnan KM. Biomedical Nanomagnetism: A Spin Through Possibilities in Imaging, Diagnostics, and Therapy. *IEEE Transactions on Magnetics*. 2010; 46(7): 2523-2558. doi: 10.1109/tmag.2010.2046907
63. Salavati-Niasari M, Salemi P, Davar F. Oxidation of cyclohexene with tert-butylhydroperoxide and hydrogen peroxide catalyzed by Cu(II), Ni(II), Co(II) and Mn(II) complexes of N,N'-bis-(α -methylsalicylidene)-2,2-dimethylpropane-1,3-diamine, supported on alumina. *Journal of Molecular Catalysis A: Chemical*. 2005; 238(1-2): 215-222. doi: 10.1016/j.molcata.2005.05.026
64. Salavati-Niasari M, Dadkhah M, Davar F. Synthesis and characterization of pure cubic zirconium oxide nanocrystals by decomposition of bis-aqua, tris-acetylacetonatozirconium(IV) nitrate as new precursor complex. *Inorganica Chimica Acta*. 2009; 362(11): 3969-3974. doi: 10.1016/j.ica.2009.05.036
65. Salavati-Niasari M, Davar F. In situ one-pot template synthesis (IOPTS) and characterization of copper(II) complexes of 14-membered hexaaza macrocyclic ligand "3,10-dialkyl-dibenzo-1,3,5,8,10,12-hexaazacyclotetradecane." *Inorganic Chemistry Communications*. 2006; 9(2): 175-179. doi: 10.1016/j.inoche.2005.10.028
66. Wu X, Ding Z, Song N, et al. Effect of the rare-earth substitution on the structural, magnetic and adsorption properties in cobalt ferrite nano-particles. *Ceramics International*. 2016; 42(3): 4246-4255. doi: 10.1016/j.ceramint.2015.11.100
67. Gupta A.K, Gupta M. Synthesis and surface engineering of iron oxide nanoparticles for biomedical applications. *Biomaterials*. 2005; 26(18): 3995-4021. doi: 10.1016/j.biomaterials.2004.10.012
68. Rai M, Yadav A, Gade A. Silver nanoparticles as a new generation of antimicrobials. *Biotechnology Advances*. 2009; 27(1): 76-83. doi: 10.1016/j.biotechadv.2008.09.002
69. Chudasama B, Vala A, Kandhariya N, et al. Enhanced antibacterial activity of bifunctional Fe₃O₄-Ag core-shell nanostructures." *Nano Res*. 2009; 2(12): 955-965. doi: 10.1007/S12274-009-9098-4/METRICS
70. Arokiyaraj S, Saravanan M, Udaya Prakash NK, et al. Enhanced antibacterial activity of iron oxide magnetic nanoparticles treated with *Argemone mexicana* L. leaf extract: An in vitro study. *Materials Research Bulletin*. 2013; 48(9): 3323-3327. doi: 10.1016/j.materresbull.2013.05.059
71. Kurtz MB and Rex J.H. Glucan synthase inhibitors as antifungal agents. *Adv Protein Chem*. 2001; 56: 423-475. doi: 10.1016/S0065-3233(01)56011-8
72. Brown DF, Kothari D. Comparison of antibiotic discs from different sources. *Journal of Clinical Pathology*. 1975; 28(10): 779-783. doi: 10.1136/jcp.28.10.779
73. Shweta G.M, Naik L.R, Pujar RB, et al. Cobalt, Copper and Magnesium Doped Nickel Zinc Nanoferrites by Solution-Combustion Method: Structural, Antibacterial and Antifungal Properties. *Journal of Metastable and Nanocrystalline Materials*. 2024; 39: 21-36. doi: 10.4028/p-zan6ns
74. Shin T.H, Choi Y, Kim S, et al. Recent advances in magnetic nanoparticle-based multi-modal imaging. *Chemical Society Reviews*. 2015; 44(14): 4501-4516. doi: 10.1039/c4cs00345d
75. Sánchez J, Cortés-Hernández DA, Rodríguez-Reyes M. Synthesis of TEG-coated cobalt-gallium ferrites: Characterization and evaluation of their magnetic properties for biomedical devices. *Journal of Alloys and Compounds*. 2019; 781: 1040-1047. doi: 10.1016/j.jallcom.2018.12.052
76. Ansari MA. Nanotechnology in Food and Plant Science: Challenges and Future Prospects. *Plants*. 2023; 12(13): 2565. doi: 10.3390/PLANTS12132565/S1
77. Kandasamy G, Maity D. Recent advances in superparamagnetic iron oxide nanoparticles (SPIONs) for in vitro and in vivo cancer nanotheranostics. *International Journal of Pharmaceutics*. 2015; 496(2): 191-218. doi: 10.1016/j.ijpharm.2015.10.058
78. Muneer R, Hashmet MR, Pourafshary P, Shakeel M. Unlocking the Power of Artificial Intelligence: Accurate Zeta Potential Prediction Using Machine Learning. *Nanomaterials*. 2023; 13(7): 1209. doi: 10.3390/NANO13071209/S1
79. Chircov C, Ștefan RE, Dolete G, et al. Dextran-Coated Iron Oxide Nanoparticles Loaded with Curcumin for Antimicrobial Therapies. *Pharmaceutics*. 2022; 14(5): 1057. doi: 10.3390/pharmaceutics14051057
80. Hashem AH, Saied E, Amin BH, et al. Antifungal Activity of Biosynthesized Silver Nanoparticles (AgNPs) against *Aspergilli* Causing Aspergillosis: Ultrastructure Study. *J Funct. Biomater*. 2022; 13(4): 242. doi: 10.3390/JFB13040242/S1
81. Ambashta RD, Sillanpää M. Water purification using magnetic assistance: A review. *Journal of Hazardous Materials*. 2010; 180(1-3): 38-49. doi: 10.1016/j.jhazmat.2010.04.105
82. Zeng S, Duan S, Tang R, et al. Magnetically separable Ni_{0.6}Fe_{2.4}O₄ nanoparticles as an effective adsorbent for dye removal: Synthesis and study on the kinetic and thermodynamic behaviors for dye adsorption. *Chemical Engineering Journal*. 2014; 258: 218-228. doi: 10.1016/j.cej.2014.07.093

83. Konicki W, Sibera D, Mijowska E, et al. Equilibrium and kinetic studies on acid dye Acid Red 88 adsorption by magnetic ZnFe₂O₄ spinel ferrite nanoparticles. *Journal of Colloid and Interface Science*. 2013; 398: 152-160. doi: 10.1016/j.jcis.2013.02.021
84. Zhang X, Zhang P, Wu Z, et al. Adsorption of methylene blue onto humic acid-coated Fe₃O₄ nanoparticles. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. 2013; 435: 85-90. doi: 10.1016/j.colsurfa.2012.12.056
85. Tolmacheva VV, Apyari VV, Kochuk EV, et al. Magnetic adsorbents based on iron oxide nanoparticles for the extraction and preconcentration of organic compounds. *Journal of Analytical Chemistry*. 2016; 71(4): 321-338. doi: 10.1134/s1061934816040079
86. Khojasteh H, Salavati-Niasari M, Safajou H, et al. Facile reduction of graphene using urea in solid phase and surface modification by N-doped graphene quantum dots for adsorption of organic dyes. *Diamond and Related Materials*. 2017; 79: 133-144. doi: 10.1016/j.diamond.2017.09.011
87. Liu J, Du C, Huang W, et al. Injectable smart stimuli-responsive hydrogels: pioneering advancements in biomedical applications. *Biomaterials Science*. 2024; 12(1): 8-56. doi: 10.1039/d3bm01352a
88. Mahmoodi NM, Bashiri M, Moeen SJ. Synthesis of nickel–zinc ferrite magnetic nanoparticle and dye degradation using photocatalytic ozonation. *Materials Research Bulletin*. 2012; 47(12): 4403-4408. doi: 10.1016/j.materresbull.2012.09.036
89. Ganjali F, Kashtiaray A, Zarei-Shokat S, et al. Functionalized hybrid magnetic catalytic systems on micro- and nanoscale utilized in organic synthesis and degradation of dyes. *Nanoscale Advances*. 2022; 4(5): 1263-1307. doi: 10.1039/d1na00818h
90. Wadhawan S, Jain A, Nayyar J, et al. Role of nanomaterials as adsorbents in heavy metal ion removal from waste water: A review. *Journal of Water Process Engineering*. 2020; 33: 101038. doi: 10.1016/j.jwpe.2019.101038